

# LUCENE<sup>TM</sup> LC170

Polyolefin Elastomer

## **Applications**

- · General purpose thermoplastic elastomer for polymer modification
- · Automotive interior/exterior, Shoe sole, Wire & Cable

#### **Description**

- LUCENE<sup>TM</sup> LC170 is an ethylene-1-octene copolymer produced using LG Chem's metallocene polymerization catalyst and solution process technology.
- LUCENE<sup>™</sup> LC170 is an excellent impact modifier for plastics and offers unique performance capabilities for compounded products.
- LUCENE™ LC170 complies with FDA regulation 21 CFR 177.1520(c)(3.2c).

## **Typical properties**

Characteristics	Test Method	Unit	Value
Physical <sup>(1)</sup>	:::	:	
Density	ASTM D1505	g/cm³	0.870
MFR(190℃,2.16kg)	ASTM D1238	g/10min	1.1
Mooney Viscosity(ML1+4@121℃)	ASTM D1646	MU	23
Mechanical <sup>(2)</sup>			
Tensile Strength at Break	ASTM D638 <sup>(3)</sup>	Мра	9.5
Elongation at Break	ASTM D638 <sup>(3)</sup>	%	>900
Tear Strength	ASTM D624	kN/m	40
FlexuralModulus1% Secant	ASTM D790	Мра	14
Hardness			
Shore hardness(Shore A)	ASTM D2240	-	71
Thermal	***************************************		
Melting Temperature	LG	${\mathbb C}$	58
Glass Transition Temperature	LG	${\mathbb C}$	-53

- (1) The properties data in this table are typical values, and not guaranteed specification.
- (2) Typical resin property values are measured on a standard compression molded specimens
- (3) Speed of 500 mm/min.

# **Processing information**

LUCENE<sup>™</sup> LC170 may be processed on conventional equipment. It is recommended that
hopper feed throat should be cooled below 30°C to prevent from pellet bridging with low
melting point.

For additional sales, order and technical assistance

Revised:11/07/2014